

ATTORNEY DOCKET
071308.0668
2003P08802WOUS

PATENT APPLICATION

FOR NATIONAL PHASE SUBMISSION


8

REMARKS

Applicants request the Examiner enter the above amendments prior to examination of this application. Applicants respectfully submit that the amendments are supported by the specification and add no new matter. Early and favorable acceptance of this national stage application is respectfully requested.

Applicants believe no fees are due at this time; however, the Commissioner is hereby authorized to charge any fees required to effectuate this filing to Deposit Account No. 50-2148 of Baker Botts L.L.P.

If there are any matters concerning this Application that may be cleared up in a telephone conversation, please contact Applicants' attorney, Andreas Grubert, at 512.322.2545.

Respectfully submitted,
BAKER BOTTS L.L.P.
Attorney for Applicants

Bruce W. Slayden, II
Reg. No. 33,790

Date:

2/10/06

SEND CORRESPONDENCE TO:

Baker Botts L.L.P.
CUSTOMER ACCOUNT NO. 31625
512.322.2606
512.322.8383 (fax)

10/567995

ATTORNEY DOCKET NO.
071308.0668
2003P08802WOUS

PATENT APPLICATION
IAP20 Rec'd PCT/PTO 10 FEB 2006

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

1

Description

METHOD FOR PRODUCING ELECTRICAL CONTACTING OF A PIEZOELECTRIC
ACTUATOR AND POLARIZATION OF THE PIEZOELECTRIC ACTUATOR

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a U.S. national stage application
of International Application No. PCT/EP2004/051775 filed
August 11, 2004, which designates the United States of
America, and claims priority to German application number
DE 10338463.3 filed August 21, 2003, the contents of which are
hereby incorporated by reference in their entirety.

TECHNICAL FIELD

[0002] The invention relates to a method for producing
electrical contacting of a piezoelectric actuator and a method
for polarizing the piezoelectric actuator ~~according to the
pre-characterizing clause of claim 1.~~

BACKGROUND

[0003] Piezoelectric actuators generally consist of
collectively sintered stacks of piezoceramic layers with
interposed metal electrodes. Every second metal electrode is
brought out on a first side and connected to a first
metallization path. On the opposite side there is provided a
second metallization path which is connected in an
electrically conducting manner to the other metal electrodes,

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

2

thereby providing two metal electrode arrangements which are electrically isolated from one another.

[0004] During operation of the piezoelectric actuators, large forces but only small relative displacements are attained, parallel to a polarization direction of the piezoceramic layers. To achieve low operating voltages, the piezoelectric actuator consists of a plurality of piezoceramic layers. To polarize the actuator, an electric polarization field is applied to the two electrode structures, thereby producing a maximum remanent polarization and an ordered distribution of the domains oriented in field direction in the crystals of the ceramic layers compared to an unpolarized initial state. Polarization is performed at a piezoceramic layer temperature above the Curie temperature of the piezoceramic layer.

[0005] For electrical contacting of the piezoelectric actuator, it is additionally necessary to contact the metallization paths to electric conductors. For this purpose the electric conductors are permanently soldered to the metallization paths in a soldering process.

[0006] European patent application EP 0 350 941 A2 discloses a piezoelectric actuator and a method for manufacturing the piezoelectric actuator which is designed in the form of a plurality of piezoceramic layers, an electrode being disposed between each of the piezoceramic layers. Every second electrode is connected in an electrically conducting manner to a metallization path which is disposed on the outside of the piezoelectric actuator. The other electrodes are connected in

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

3

an electrically conducting manner to a second metallization path which is disposed opposite the first metallization path on the outside of the piezoelectric actuator. For a connection process, the piezoelectric actuator is heated above the Curie temperature so that a chemical bond is formed between the electrodes and the piezoceramic layers. In a following cooling process, polarization of the piezoceramic layers is performed, the temperature of the piezoceramic layers still being above the Curie temperature. In a subsequent soldering process, electric conductors are soldered to the metallization paths.

[0007] German patent application DE 100 26 635 A1 describes a method for producing a soldered joint between an electrical contact area of a piezoceramic actuator and a wire surface, wherein metallization strips of the piezoelectric actuator are soldered to wires disposed in parallel. Soldering takes place after polarization of the piezoceramic actuator. During the soldering process, the piezoceramic actuator is at a temperature below the Curie temperature.

SUMMARY

[0008] The object of the invention is to provide a method for producing electrical contacting of a piezoelectric actuator and a method for polarizing the piezoelectric actuator that can be carried out more quickly.

[0009] The object of the invention is achieved by a method for producing electrical contacting of a piezoelectric actuator and for polarizing the piezoelectric actuator, the method

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

4

comprising the steps of providing an actuator having at least one piezoceramic layer which has two spaced electric contacts, soldering electric conductors to the electric contacts, and heating the piezoelectric actuator up to a soldering temperature during the soldering process, wherein during the soldering process a polarizing voltage is applied to the conductors and the piezoceramic layer is polarized.

[0010] A solder material can be used whose soldering temperature is above the Curie temperature of the piezoceramic layer. The polarizing voltage can also be applied during a cooling process, and the voltage can be limited to a maximum value during cooling of the actuator. The polarizing voltage can be applied during a heating process before a maximum temperature is reached, and the current can be limited to a maximum value during heating of the actuator. The voltage present during polarization can be recorded and evaluated in order to assess the polarization and/or the actuator. The current flowing during polarization can be recorded and evaluated in order to assess the polarization and/or the actuator. The conductors can be pressed onto soldering surfaces of the contacts via heating blocks, and the heating can block at least partially heat up the actuator. A plurality of actuators can be soldered to conductors and can be polarized simultaneously. The conductors of a contact can be used monolithically for a plurality of actuators during soldering and polarization, and after soldering and polarization the conductors can be divided into individual

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

5

conductor pieces for each actuator. The conductors can be connected to contact pins prior to soldering and polarization. The actuator can be heated up to above the Curie temperature of the piezoceramic layer during the soldering process~~the method according to claim 1.~~

[0011] The advantage of the method ~~according to claim 1~~ is that the electrical contacting of the piezoelectric actuator and the polarizing of the piezoelectric actuator can be performed in a shorter time. This advantage is achieved by performing the electrical contacting and polarization at least partly simultaneously. The soldering process is preferably carried out above the Curie temperature and the polarization of the piezoceramic layers of the actuator is performed at the same time.

[0012] ~~Further advantageous embodiments of the invention are set forth in the dependent claims.~~ In an advantageous development of the method according to the invention, the polarizing voltage is also applied during a cooling phase to below the Curie temperature and limited to a maximum value, thereby ensuring on the one hand that the polarization is reliably retained and, on the other, avoiding damaging the piezoceramic layers.

[0013] In a further embodiment of the method according to the invention, the polarizing voltage is applied even before a maximum temperature is attained and the current flowing is limited to a maximum value during the heating of the actuator. This means that polarization is achieved even before reaching

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

6

the maximum temperature of the piezoelectric actuator and at the same time damage to the piezoceramic layers is reliably avoided by limiting the current to a maximum value. In a further preferred embodiment, the voltage applied during polarization is recorded and evaluated in order to be able to gauge the quality of the polarization or the quality of the piezoelectric actuator.

[0014] In a further preferred embodiment, the current flowing during polarization is recorded and evaluated in order to assess the polarization and/or the piezoelectric actuator.

[0015] In a preferred embodiment, the conductors are pressed onto soldering surfaces of the contacts via heating blocks, the heating blocks at least partially heating the actuator. In this way the soldering process is facilitated by the mechanical pressing-on of the conductors and, in addition, the temperature is applied in the region of the soldered joint, thereby achieving an improvement in the soldering process.

[0016] In another advantageous embodiment, a plurality of actuators are simultaneously soldered to conductors and polarized, thereby achieving an efficient implementation of the method so that mass production is possible.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] The invention will now be explained in greater detail with reference to the accompanying drawings, in which:

[0018] Figure 1 shows a piezoelectric actuator;

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

7

[0019] Figure 2 shows a cross-section through an edge region of the piezoelectric actuator after the soldering process;

[0020] Figure 3 schematically illustrates an arrangement for implementing the method according to the invention; and

[0021] Figure 4 shows a timing diagram for the various parameters during implementation of the method according to the invention.

DETAILED DESCRIPTION

[0022] Figure 1 schematically illustrates a piezoceramic actuator 1 having a piezoceramic component 2 with a plurality of piezoceramic layers 3 (Figure 2). Between every two layers 3 there is formed a planar electrode 4 (Figure 2). The electrodes 4 are connected in an electrically conducting manner via wires 5 to a first or a second contact pin 6, 7. Every second electrode 4 is connected in an electrically conducting manner via a wire 5 to the first contact pin 6. The other electrodes 4 are connected in an electrically conducting manner via wires 5 to the second contact pin 7. In this way a layer structure is implemented wherein each piezoceramic layer 3 is bounded by two electrodes 4 which are connected in an electrically conducting manner to different contact pins 6, 7. By applying different voltage potentials to the first and the second contact pin 6, 7, all the piezoceramic layers 3 are subject to the same voltage, so that the layers 3 expand according to the voltage applied.

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

8

[0023] Figure 2 shows a partial cross-section of an edge region of the piezoceramic component 2. On the piezoceramic component there is deposited a first metallization path 8. The first metallization path 8 is connected in an electrically conducting manner to every second electrode 4. Opposite the first metallization path 8 there is disposed on the other side of the component 2 a second metallization path 9 which is connected in an electrically conducting manner to the other electrodes 4. The metallization path 8 is connected to the wires 5 in an electrically conducting manner via a solder coating 13. The wires 5 of the first metallization path 8 are routed to the first contact pin 6.

[0024] In a corresponding manner, the second metallization path 9 is connected in an electrically conducting manner via wires 5 to the second contact pin 7.

[0025] Figure 3 shows a schematic arrangement for carrying out the method according to the invention.

[0026] For manufacturing the piezoelectric actuator 1, the layers 3 and the electrodes 4 are first produced in a sintering process. It is additionally necessary to perform polarization of the piezoceramic layers 3. For this purpose a polarizing voltage is applied to the layers 3 via the electrodes 4, the piezoceramic layers 3 having a temperature exceeding the Curie temperature of the piezoceramic layers 3. It is additionally necessary to connect electric conductors 10, 11 to the metallization paths 8, 9.

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

9

[0027] In the method according to the invention, three piezoelectric components 2 are disposed in the embodiment shown. The components 2 already possess the piezoceramic layers 3, the electrodes 4 and the metallization paths 8, 9. The metallization paths 8, 9 are disposed on opposite sides and at diametrically opposed corner regions of the component 2 which is implemented with a square cross-section. First and second conductors 10, 11 are placed on the first and second metallization path 8, 9. The first and the second conductors 10, 11 are implemented in the form of wires and connected in an electrically conducting manner to a voltage source 12. The ends of the conductors 10, 11 are in stand-off blocks 14.

[0028] The components 2 are heated up to a temperature which is above the Curie temperature of the piezoelectric layers 3. The conductors 10, 11 are then pressed against the first and second metallization path 8, 9. In addition, solder 13 is inserted between the first and the second metallization path and the first and second conductor 10, 11. Solder 13 having a soldering temperature above the Curie temperature is used as solder material. Heating elements 15 are preferably used for pressing on the first and the second conductor 10, 11 and, in addition to pressing against the first and the second conductor 10, 11, at least partially heat up the component 2 at the same time. In a preferred embodiment, the solder 13 is inserted in the form of a solder foil 16 between the metallization paths 8, 9 and the first and second conductors 10, 11.

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

10

[0029] Simultaneously with the soldering process, a polarizing voltage is applied to the conductors 10, 11 via the voltage source 12, thereby causing the piezoelectric layers 3 to be polarized. For polarization, field strengths of 1 to 2 kV/mm are used. The current values employed are a few A/cm². The polarization is preferably applied even before the maximum temperature of the component 2 is reached. In addition, the polarizing voltage is preferably maintained when the component 2 cools down from the maximum temperature to below the Curie temperature. To ensure that the current intensity does not exceed the maximum current during heating of the component 2, the current intensity is limited to a maximum value by the voltage source 12. At the same time, the voltage present is limited to a maximum value by the voltage source 12 when the component 2 is cooled down in order to ensure that the piezoceramic layers 3 are not damaged.

[0030] The conductors 10, 11 are or will be soldered to the first or second contact pins 6, 7. After the soldering and polarizing process, the conductors 10, 11 are separated to produce individual actuators 1 according to Figure 1.

[0031] Figure 4 shows a timing diagram for the polarization voltage U and the polarization current I. Also given in the diagram are the temperature T_O on the surface of the metallization paths 8, 9 and the temperature T_K of the piezoceramic layers 3. The Curie temperature for the piezoelectric layers 3 and the soldering temperature for the

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

11

soldering material used have been entered on the diagram. The characteristics have been plotted over time t in the diagram.

[0032] At the start of the polarization and soldering process, the conductors 10, 11 are pressed against the metallization paths 8, 9, the component 2 is not yet heated up and the voltage source 12 has not yet applied a polarizing voltage.

[0033] At a first instant t_1 the polarizing voltage U is applied. The components 2 are simultaneously heated up via the heating blocks 15. At a second instant t_2 the temperature T_K of the piezoceramic layer 3 reaches the Curie temperature. As the temperature rises, the conductivity of the piezoceramic layers 3 increases so that the current I rises and the voltage U falls. At a third instant t_3 the surface temperature T_O of the components 2 reaches the soldering temperature so that the soldering process commences. The soldering temperature is higher than the Curie temperature. At a fourth instant t_4 the soldering process is complete and the heating blocks 15 are switched off so that the component 2 cools down. During the time period between the third instant t_3 and the fourth instant t_4 the maximum current flowing is limited. After the fourth instant t_4 both the surface temperature T_O and the temperature T_K of the piezoceramic layer 3 begin to fall. The reduction in temperature causes the resistance of the piezoceramic layers 3 to increase so that the voltage U increases again. The voltage source 12 ensures that the polarization voltage U does not exceed a maximum value.

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

12

Appropriate voltage regulation is provided for this purpose in the voltage source 12.

[0034] Below the Curie temperature there is produced at a fifth instant t_5 a charge pulse which is reflected in a transient increase in the current intensity I . the charge pulse can be used to assess the piezoelectric actuator 1. The charge pulse is preferably compared with a reference charge pulse. If the measured charge pulse exceeds or undershoots the reference charge pulse by a specified value, the piezoelectric actuator is identified as defective. In another preferred embodiment, reference curves for the polarization voltage during the polarization and soldering process are stored in a control unit 17. The control unit 17 compares the voltage curve and/or the current curve present during the soldering and polarization process with the stored voltage curve or the stored current curve. On the basis of the comparison it is possible to assess the quality of the polarization and/or the quality of the piezoelectric actuator 1. If the measured voltage curve or the measured current curve deviates from the stored voltage curve or current curve by more than a specified value, the actuator 1 is identified as defective. If the actuator 1 is identified as defective, the actuator 1 is rejected and not processed further.

ATTORNEY DOCKET NO.
071308.0668
2003P08802WOUS

PATENT APPLICATION

SUBSTITUTE SPECIFICATION
FOR NATIONAL PHASE SUBMISSION

MARKED UP VERSION

13

ABSTRACT

[0035] ~~Disclosed is a~~ method for creating a soldered joint to contacts of a piezoelectric actuator and polarizing the piezoceramic layers of the piezoelectric actuator[[.]] has the steps of Polarization and soldering of the joint ~~are done~~ which are performed simultaneously such that the duration of the process is reduced.